TECHNICAL FEATURES

COLOURED-BODY GLAZED STONEWARE according to ANSI A137.1 (Glazed Porcelain Tiles - P1 Class)

TECHNICAL FEATURES		TEST METHOD	REQUIRED VALUES	AVERAGE VALUES
;;;;; ∱	WATER ABSORPTION	ASTM C373	≤ 0,5%	CONFORMS
1	BREAKING STRENGTH	ASTM C648	≥ 250 lbf	425 lbf 10 mm
PEI	SURFACE ABRASION RESISTANCE	ASTM C1027	As indicated by manufacturer	PEI 5: COTTON, YARN, ROPE, WOOL PEI 4: QUILT
	LINEAR THERMAL EXPANSION	ASTM C372	No provision	$\alpha \le 8 \times 10^{-8} ^{\circ} \text{C}^{-1}$ $\alpha \le 4.4 \times 10^{-6} ^{\circ} \text{F}^{-1}$
*	STAIN RESISTANCE	ASTM C1378	As indicated by manufacturer	A RESISTANT
6	CHEMICAL RESISTANCE ^(*)	ASTM C650	As indicated by manufacturer	A RESISTANT
*	FROST RESISTANCE	ASTM C1026	As indicated by manufacturer	RESISTANT
	BOND STRENGHT	ASTM C482	≥ 50 PSI	CONFORMS
	SLIP RESISTANCE	ANSI A326.3	¥	DCOF ≥ 0.42
	SHADE VARIATION	ANSI A137.1	As indicated by manufacturer	V2 Slight variation
ð	FLAME SPREAD	ASTM E84		Class A
#	THERMAL CONDUCTIVITY	EN 12524	•	λ = 1,3 W/m °K / 0.7 BTU/ft h °F
7	RECOMMENDED MINIMUM JOINT ^(*)	RECT (INDOOR)	•	2 mm
-	THICKNESS	SIZES		
1		24"x24" Rect - 60x60 cm	(2)	10 mm
	•	12"x24" Rect - 30x60 cm	8	
		8"x24" Rect - 20x60 cm	•	

^(*) Excluding hydrofluoric acid and its derivatives

PACKINGS AND WEIGHTS

SIZES	SF / CTN	LINEAR FT / CTN	PIECES / CTN	CTN / PALLET	SF / PALLET	LBS / CTN 71.65	LBS / PALLET 2,292.8
24"x24" Rect							
12"x24" Rect	13.67	-	7	32	437.44	62.83	2,010.56
8"x24" Rect	11.95		9	36	430.20	53.57	1,928.52
MOSAIC BASKET WEAVE 12"x12" Rect	5.01	-	5	90	450.90	21.50	1,935
HERRINGBONE MODULUS A-B 95/8" x24" Rect	5.54	-	6	35	193.9	27.60	966
BULLNOSE 31/1m x12"	4.65	17.72	18	112	520.8	18.78	2,103.36

^(**) The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards